




## ARABESK

Water-based decorative coloured pearlescent effect finish  
INTERIOR



### DESCRIPTION

Arabesk is a water-based decorative effect finish.

### FIELD OF USE

It is designed for interior decoration, giving a coloured, pearlescent effect on walls.  
It is especially suitable for big surfaces like halls, dining rooms and flats.

### TECHNICAL CHARACTERISTICS

- Aspect : Coloured Pearlescent effect.
- Colours : See our catalogue.
- Spreading-rate : 7 to 8 m<sup>2</sup>/Kg, complies with ISO 23811 (2009).
- Density : 1.12 Kg/L +/- 0.05 depending upon the colour 25° C, complies with NM ISO2811-1(2008).
- Viscosity : 108 KU's +/- 10 to 25° C (Kreb Stormer), complies with ASTM D561 (1991).

### SURFACE PREPARATION

For easy application and optimum performance the surface needs to be clean, sound and dry before rendering :

- \* Sand vigorously with a Chiendent brush.
- \* Sand with sandpaper.
- \* Remove the dust.
- \* Wash with a water-jet if necessary.

### APPLICATION PROPERTIES

Using a roller, apply an even coat of Colofondo. over the surface. Let the Colofondo dry for 12 hours.  
Using the special brush, apply Arabesk in all directions over the surface. To reduce the risk of lapping problems, work in areas of 1 to 2 m<sup>2</sup>.  
Leave the product for approximately ten minutes to dry.  
Using a blade or rendering tool, spread out the Arabesk in order to obtain the special effect.  
Do not apply on cold wet walls below 5°C or conditions of high relative humidity (> 70%).

### APPLICATION DETAILS FOR USAGE

Dilution : This product is ready for application. Do not dilute. Mix well before use.

### DRYING TIME

Drying time at 20°C and 60% relative humidity:  
\*Touch dry : 3 to 4 hours.  
\*Dry : 24 hours.  
\*Washable : 20 days.

### RECOMMENDED SYSTEM (consult us)

#### ■ INTERIOR

SYSTEM	NUMBER OF COATS
COLOPRIM	1
COLENDUIT EXTRA B505 ou SP88	2
COLOSTOP	1
COLOFONDO	1
ARABESK	1

### STORAGE

Two years in the closed plastic container, as delivered.  
Store inside in conditions avoiding extremes of hot and cold temperatures.

### PACKAGING

ARABESK : 2,5 Kg.  
COLOFONDO : 4 kg (Spreading-rate 6 à 7 m<sup>2</sup>/kg).

### HEALTH & SAFETY

This product is not classified as dangerous under current regulations.  
Fore more details, consult the safety data sheet N° 27.

Edition : October 2016 by Colorado (10/16).  
This version replaces all previous editions.

N.B : The changing needs of our customers as well as technical progress may lead us to change the characteristics of our products without notice and without liability.

COLORADO is certified ISO 9001, ISO 14001 & OHSAS 18001