



COLOCAR

DESCRIPTION

Fast drying, nitro cellulose-based high-build topcoat.

AREAS OF USE

Colocar is suitable for all new and/or old automotive and industrial surfaces.

CHEMICAL COMPOSITION

Nitro-cellulose based laquer.

GENERAL CHARACTERISTICS

High build finish with good filling properties and fast drying.

PHYSICAL PROPERTIES

- Density : 0,98 to 1,3 (Kg/L)
- Viscosity : 80 ± 10 (Sec DIN6)
- Volume solids : 45 (%)
- Weight solids: 50 (%)
- Colour : every colour is available
- Spreading-rate : 8 m²/Kg/50 µm

APPLICATION DETAILS FOR USE

- Mixture ratio : 100 : 80 to 90 (Laquer : diluent)
- Application viscosity (DINCUP 4mm 20°C) : 18-20 Sec (dilution up to 90% with C3 or cellulosic diluent)

PACKAGING

Product available in 0,25kg, 0,5Kg, 1Kg and 20Kg.

DRYING



Evaporation time at 25°C : 5-10 minutes



Drying time at 20°C : 15-20 minutes

APPLICATION CONDITIONS

- Mixing ratio : 100 : 80 à 90 (Laquer : diluent)
- Application viscosity (DINCUP 4mm 20°C) : 18-20 Sec (dilution up to 90% with C3 or cellulosic diluent)

	Opening of the spraygun (mm)	Pressure of the spraygun (bars)
Spray	1.3-1.6	3.5-4.5
Airless spray	1.4-1.7	3.5-4.5
HVLP	1.3-1.8	
HE	1.2-1.8	According to the supplier
Number of coats/ thickness (µm)		1-3/40-80

STORAGE

1 year in the closed original container. Store inside in conditions avoiding extremes of hot and cold temperatures.

HEALTH AND SAFETY

Dangerous and easily flammable. for more information, consult the safety data sheet N° 100.