



DAHAB

Water-based decorative effect finish
INTERIOR



DESCRIPTION

A water-based decorative coating based upon modified, synthetic resins with metallic sand and scintillating effects.

FIELD OF USE

It is designed for interior decoration, giving a subtle, refined finish and a warm atmosphere.

TECHNICAL CHARACTERISTICS

- Aspect : Metallic sand and gold scintillating effects.
- Colours : See our catalogue.
- Spreading-rate : About 7,5 m²/L (in one coat applied by brush, roller or sponge), complies with ISO 23811 (2009).
- Density : 1.18 Kg/L +/- 0.05 at 25° C, complies with NM ISO2811-1(2008).
- Viscosity : 33500 cP +/- 2500 cP at 25° C.

SURFACE PREPARATION

For easy application and optimum performance the surface needs to be clean, sound and dry before rendering :

- * Sand vigorously with a Chiendent brush.
- * Sand with sandpaper.
- * Remove the dust.
- * Wash with a water-jet if necessary.

APPLICATION PROPERTIES

For easy application and optimum performance the surface needs to be clean, sound and dry before rendering.

Using a roller, apply an even coat of Colofondo (Tinted) over the surface. Let the Colofondo dry for 12 hours. Using the special short pile roller, apply DAHAB (diluted with 5% of water) in all directions over the surface. To reduce the risk of lapping problems, work in areas of 1 to 2 m².

Leave the product to dry, before applying a second diluted coat (and if necessary a third coat) using the short pile roller. Using a blade or rendering tool, spread out the DAHAB in order to obtain the special effect. Do not apply on cold wet walls below 5° C or conditions of high relative humidity (> 70%).

APPLICATION DETAILS FOR USAGE

Dilution : This product is ready for application. Mix well before use.
Depending upon the application method used, this product can be diluted with upto 5% of tap water

DRYING TIME

Drying time at 20°C and 65% relative humidity:
*Touch dry : 1 hour.
* Dry : 5 hours.
*Washable : 20 days (with one coat of Coloprime).

RECOMMENDED SYSTEM (consult us)

■ INTERIOR

SYSTEM	NUMBRE OF COATS
COLOPRIM	1
COLENDUIT EXTRA B505 ou SP88	2
COLOVINYL 600	1
COLOFONDO	1
DAHAB	2
COLOPRIM (For wash resistance)	1

STORAGE

12 months in the closed plastic container, as delivered. Store inside in conditions avoiding extremes of hot and cold temperatures.

PACKAGING

- *DAHAB : 2,5 kg.
- *COLOFONDO : 1.6 litres.

HEALTH & SAFETY

This product is not classified as dangerous under current regulations.
Fore more details, consult the safety data sheet N° 155.

Edition : October 2016 by Colorado (10/16).
This version replaces all previous editions.

N.B : The changing needs of our customers as well as technical progress may lead us to change the characteristics of our products without notice and without liability.

COLORADO is certified ISO 9001, ISO 14001 & OHSAS 18001