TECHNICAL DATA SHEET



KASBAA

Decorative effect coating based on natural fibers

INTERIOR



DESCRIPTION

Thick, pasty, traditional water-based product without any odour.

Improves the thermal insulation and soundproofing properties of interior walls.

Has easy application properties and covers up any surface defects.

FIELD OF USE

Recommended for application to interior walls.

TECHNICAL CHARACTERISTICS

- Aspect : Pasty product.
- Colours : White, can be waxed with the different colours available in our catalogue for Kasbaa Cire.
- Spreading-rate : * Kasbaa : 1.3 à 1.8 Kg/m².
 * Cire : 12 à 15 m²/L. Complies with ISO 23811 (2009).
- Density kg/l at 25°C : * Kasbaa : 1.69 +/- 0.05.
 * Cire : 1 +/- 0.05. Complies with NM ISO2811-1(2008).
- Viscosity at 25 °C : * Kasbaa : 1000 +/- 200 poises.
 * Cire : 100 +/- 5 KU.

SURFACE PREPARATION

For easy application and optimum performance the surface needs to be clean, sound and dry before rendering :

- * Sand vigorously with a Chiendent brush.
- * Sand with sandpaper.
- * Remove the dust.
- * Wash with a water-jet if necessary.

APPLICATION PROPERTIES

For easy application and optimum performance the surface needs to be clean sound and dry. Do not apply on cold wet, walls below 5°C or in conditions of high relative humidity (>70%).

APPLICATION DETAILS FOR USAGE

Dilution : Ready for use. Do not dilute.

SDRYING TIME

*Kasbaa : 24 hours. *Cire : 30 to 45 mn.

RECOMMENDED SYSTEM (consult us)

INTERIOR

SYSTEM	NUMBER OF COATS
COLOPRIM	1
COLENDUIT EXTRA B505/SP88	1
COLOVINYL 600	1
KASBAA	1
KASBAA CIRE	1

STORAGE

Two years in the closed paint can, as delivered. Store inside in conditions avoiding extremes of hot and cold temperatures.

PACKAGING

- * Kasbaa : 5 kg and 25 kg.
- * Cire : 0,8 kg (800 ml).

HEALTH & SAFETY

This product is not classified as dangerous under current regulations. For more details, consult the safety data sheet N° 25.

Edition : October 2016 by Colorado (10/16). This version replaces all previous editions.

N.B: The changing needs of our customers as well as technical progress may lead us to change the characteristics of our products without notice and without liability.

www.colorado.sa