



STARFILLER

Hydraulic powder coating for exterior renders



DESCRIPTION

Powdered render based on a hydraulic binder and special extenders.
Complies with French standard NF EN 1062-1.

FIELD OF USE

Designed for retouching and finishing work on exterior masonry.

TECHNICAL CHARACTERISTICS

- Aspect : Powder. V.O.C = 0 g/l (EU Directive 2004-42).
- Colour : White.
- Spreading-rate : 2 to 3 kg / m², complies with ISO 23811 (2009).

SURFACE PREPARATION

For easy application and optimum performance the surface needs to be clean, sound and dry before rendering :

- * Sand vigorously with Chiendent brush.
- * Sand with sandpaper.
- * Remove the dust.
- * Wash with a water-jet if necessary.

APPLICATION PROPERTIES

Recommended hardware: coating knife.
If the surface is wet, eradicate the cause of the humidity and apply one coat of a water-proofing primer Coloprime . Once dry, apply by trowel a thin coat of Starfiller, in order to repair any holes and obtain uniform surface.
Limitation of use : Do not apply on condensant or frozen support at temperature below 5 ° C, nor relative humidity above 70%.

APPLICATION DETAILS FOR USAGE

Water.

DRYING TIME

Drying at 20°C and 60% of humidity :

- * Touch Dry : 15min.
- * Through Dry : 12 hours.
- * Recoat : 24 hours.

Up to 2 cm in 2 coats (1 cm per coat).

RECOMMENDED SYSTEM (Consult us)

■ EXTERIOR

SYSTEM	NUMBER OF COATS
STARFILLER	2
COLOSHIELD PRIMER	1
COLOSHIELD ou COLOMAX	2

STORAGE

Two years in the closed original container. Store inside in conditions avoiding extremes of hot and cold temperatures.

PACKAGING

25 kg

HEALTH & SAFETY

This product may cause allergic reaction.
For more details, consult the safety data sheet N° 174.

Edition : April 2017 by Colorado (04/17).
This version replaces all previous editions.

N.B : The changing needs of our customers as well as technical progress may lead us to change the characteristics of our products without notice and without liability.

COLORADO is certified ISO 9001, ISO 14001 & OHSAS 18001