



WASH PRIMER

DESCRIPTION

WASH PRIMER is an anti-corrosion primer with excellent adhesion for all types of metal, especially Aluminum and galvanized steel.

It's catalyzed by acid.

END-USE AND PROPERTIES

Designed for excellent adhesion and anti-corrosion resistance in industrial and car-refinishing applications for interior and exterior use.

COATING PROPERTIES

- Aspect : Smooth, flat
- Tint : Greenish yellow
- Spreading-rate : 18 – 20 m²/L by coat.
- Density: Base: 1.10 +/- 0,05 Kg/L à 25°C
Catalyst: 0.86 0,05 Kg/L à 25°C

SURFACE PREPARATION

The product is applied in one coat by air spray over the well prepared support (sand blasted, dry, grease and dust-free after brushing).

APPLICATION PROPERTIES

Application: Air spray

Mixing Ratio: the two components need to be mixed in the following ratio: 9 of the base and 1 of the catalyzer (by volume).

Reaction time: use immediately after mixing.

Pot life of the mixture: 8 hours. After this period, the product will thicken and become impossible to use.

Do not apply on cold, wet supports bellow 5°C or in conditions of high relative humidity, greater than 70%.

Substrate conditions: for a quick and easy application the surface should be sound, dry and well prepared.

Eliminate the causes of the humidity before starting to remedy its effects.

RECOMENDED SYSTEMS

WASH PRIMER can be covered by all types of undercoats and topcoats.

Dilution

Ready to use.

Use D33 or D55 to clean.

Drying time

*Touch dry :10 minutes

* Through dry : 20 minutes

STORAGE

12 months in the closed paint can, as delivered.

Store inside in conditions avoiding extremes of hot and cold temperatures.

Keep away from sources of heat, sparks and flames.

PACKAGING

Kit: 0.9 L of base.

0.1 L of catalyzer

HEALTH, SAFETY AND ENVIRONMENT.

Warning! The catalyzer contains Phosphoric acid.

Wear safety glasses and protective gloves during the mixture of the two components.

Flammable product, use in a well ventilated area.

Consult the safety data sheet for more information.

Edition : Fevrier 2016 par Colorado (DC 28 D).
Cette version annule et remplace les précédentes.